



technical data sheet

BOSTIK ROOF & GUTTER COLOUR SILICONE

PRODUCT

Bostik Roof & Gutter Colour Silicone is a high performance, ultra violet resistant one component neutral cure silicone sealant.

DESCRIPTION

Bostik Roof & Gutter Colour Silicone is an industrial grade neutral cure silicone sealant designed for sealing lap joints in metal guttering, aluminium roofing, flashings and down pipes. Specifically designed to meet Australian conditions and to match coloured decorative finishes.

RECOMMENDED USES

- Metal Roofing Systems
- Flashing & down pipes
- Lap joints in zincalume, colourbond and other BHP decorative sheet metal
- Skylights & extraction units
- Pipe or sprinkler system penetrations
- Air conditioning
- Sheet-metal,
- General purpose adhering & sealing, building materials, steel, aluminium, concrete, brick and masonry
- Block or brickwork

FEATURES & BENEFITS

- Suitable for coloured roofing systems
- Excellent General Purpose Sealant
- Permanently flexible
- Suitable for interior and exterior applications
- Unaffected by rain, snow, extreme temperature change and constant ultra violet exposure
- Waterproof
- Excellent adhesion properties

PERFORMANCE PROPERTIES

Typical properties after 7 days cure at 25°C and 50% RH.

| | |
|---|-----------------|
| Tooling time (at 20°C) | 3 - 5 minutes |
| Tack free time (Per Fed. Spec TTS001543A) | 10-15 minutes |
| Cure time (to 10mm depth @ 23°C & 50% RH) | 5 - 7 days |
| Application range | 10°C to 60°C |
| Temperature Performance range | - 62°C to 177°C |
| Hardness shore A (ASTM D-2440) | 23 |
| Tensile strength (ASM D-412) | 1.2MPa |
| Sag, slump (Per TT-S-001543A) | Nil |
| Specific gravity | 1.0 |
| Cure method (Chemical type) | Neutral |
| UV and ozone resistance | Excellent |
| Joint movement | ± 25% |

PACKAGING

Roof & Gutter Colour Silicone is available in 300g cartridges in cut case carton lot of 6.

COVERAGE

Approximately 13 lineal metres per 300ml cartridge based on an average joint size of 5mm depth and 5mm width.

APPLICATION INSTRUCTIONS

Surface Preparation:

Surfaces to be sealed must be clean, dry and free of wax, grease or any loose or flaking paint. For optimum adhesive bond, clean surface with alcohol or acetone wipe, allow to dry.

Application

- Use masking tape each side of joint to simplify clean up, to protect surfaces and to ensure a neat job. Complete all painting before applying.
- Insert a sealant support material such as polyurethane foam into deep joints or gaps to ensure sealant depth is no greater than 10 mm.
- Cut nozzle at 45° angle to desired thickness. Cut diaphragm on cartridge. Insert cartridge into caulking gun. Hold gun at 45° angle with nozzle in contact with both sides of joint. Apply by pushing sealant ahead of nozzle, thus ensuring sealant is pushed firmly into place.
- Smooth off before skin forms (within 10 minutes). Remove excess sealant immediately with a cloth dampened with mineral turpentine. If used, remove masking tape immediately sealant tooling is complete. Sealant surface skins in 10 minutes and is touch dry in 30 minutes.
- Cured sealant can be removed by trimming with a sharp blade but avoid under cutting seal.
- After use, cured plug will form in cartridge nozzle, before re-using remove plug and extrude sealant.
- Entire cartridge contents should be used within 12 months.

PRIMING

- On metal, steel and non-porous surfaces primer is not required.
- On porous or absorbent surfaces such as natural stone, granite etc, Bostik Primer must be used (consult Bostik Technical Department).

MIXING

Ready to use straight from the cartridge.

PRECAUTION

Not recommended for use in horizontal walkways exposed to high abrasion (pedestrian traffic), in totally confined areas or below grade or in expansion joints that will encounter continuous water immersion.

- Not to be used for structural glazing applications.
- Not to be used on extruded type polycarbonates or polyacrylates if they are under tension as stress cracking may occur.
- Not recommended for below water line applications.
- Do not apply to wet surfaces.
- Not recommended for marble, granite or stone.

PAINTABILITY

Not paintable

P.A.T.S (Pretested Adhesion To Substrate) Programme

Bostik offer a service in which a program has been established to eliminate potential field problems by pre-testing Bostik adhesives with samples of building materials to which the adhesive will be applied. This service is available on large projects where pre-application testing will aid in determining the proper surface preparation method to achieve optimum adhesion. Consult a Bostik representative for further information.

HEALTH AND SAFETY

On contact, uncured sealant causes irritation.

- Gloves and protective goggles must be worn during application and use.
- Avoid contact with skin, eyes and avoid breathing in vapour.
- Wear protective gloves when mixing or using
- If poisoning occurs, contact a doctor or Poisons Information Centre.
- If swallowed, do not induce vomiting. Give a glass of water.
- If skin contact occurs, remove contaminated clothing and wash skin thoroughly for a minimum of 15 minutes and see a doctor.

- For more detailed information refer to Material Safety Data Sheet.

CLEAN-UP

Wipe off excess sealant immediately and clean up with mineral turpentine

STORAGE

- Store inside where possible out of direct sunlight and heat.
- Store below 25°C
- Shelf life is 12 months in unopened container when stored below 25°C.

FIRE

Bostik Roof and Gutter Silicone is non-flammable.

BOSTIK ROOF & GUTTER COLOUR SILICONE

| Item No. | Stock Size / Colour | Units P/Ctn |
|----------|--------------------------------|-------------|
| 329770 | 300g Cartridge Classic Cream | 6 |
| 329800 | 300g Cartridge Manor Red | 6 |
| 329789 | 300g Cartridge Pale Eucalypt | 6 |
| 329797 | 300g Cartridge Cottage Green | 6 |
| 329762 | 300g Cartridge Surfmist | 6 |
| 329827 | 300g Cartridge Woodland Grey | 6 |
| 329819 | 300g Cartridge Stone | 6 |
| 329843 | 300g Cartridge Deep Ocean | 6 |
| 329835 | 300g Cartridge Galvanised Grey | 6 |
| 329851 | 300g Cartridge Night Sky | 6 |

The representations and recommendations regarding the products are based on tests which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Australia Pty Ltd be liable to anyone except for replacement of the products or refund of the purchase price.

ALL SALES ARE EXPRESSLY LIMITED TO THE TERMS AND CONDITIONS OF SALE OF BOSTIK AUSTRALIA PTY LTD



BOSTIK AUSTRALIA PTY LTD
Phone: +61-3-9279 9333
Fax: +61-3-9279 9240

SYDNEY
Phone: 02 8825 3488
Fax: 02 8825 3411

BOSTIK NZ LIMITED
Phone: +64-4-567 5119
Fax: +64-4-567-5412

ADELAIDE
Phone: 08 8244 0511
Fax: 08 8244 0522

FOR FURTHER INFORMATION

BOSTIK SINGAPORE PTE LTD
Phone: +65-6863 4088
Fax: +65-6863 4077

PERTH
Phone: 08 9258 6218
Fax: 08 9258 7687

(ABN 79 003 893 838)

BOSTIK (MALAYSIA) SDN BHD
Phone: +606 764 3246
Fax: +606 764 3248

BRISBANE
Phone: 07 3260 2206
Fax: 07 3260 2123

| | |
|--------------|-------------------------------|
| Product: | Roof & Gutter Colour Silicone |
| Issue Date: | March 2007 |
| Issue No: | 4 |
| Division: | Plumbing |
| Total Pages: | 2 |